
Renotex C

Impregnated, thermoplastic, economic and firm to hard counter material. It is on needle punched non-woven with a very good shape reproduction. The material can be used for ladies, men and children shoes e.g. in lower grades for formal shoes and higher grades for heavy shoes like working boots, tracking shoes etc.

Adhesive: both side bonding // coated with EVA adhesive

Types:	Thickness:
Renotex C 80	0.75 - 0.85 mm
Renotex C 100	0.95 - 1.05 mm
Renotex C 110	1.05 - 1.15 mm
Renotex C 120	1.15 - 1.25 mm
Renotex C 130	1.25 - 1.35 mm
Renotex C 150	1.45 - 1.55 mm
Renotex C 160	1.60 - 1.70 mm
Renotex C 180	1.75 - 1.85 mm
Renotex C 200	1.95 - 2.05 mm

Method for use: “Hot-Cold”
Required interface temperature for bonding: approx. 90 -100°C
Activating temperature: approx. 120 -150°C
Time: approx. 15 - 40 sec.

Advice: All data may vary according to the substance of the material and the type of upper.

Delivery: Sheets, 1.00 x 1.50 m

Cutting: In length direction

Skiving: We recommend a rippled steel bottom roller and a suitable skiving foot

Manufacturers warranty: Due to the great number of materials being used for shoe manufacturing the possibilities of chemical reactions and incompatibilities between components should be always tested beforehand. We are not liable for damages arising by non observance of our instructions for applications or from reactions beyond our influence and control.

Storing: Under normal conditions the storage is unlimited. Avoid direct storing in the sun. We guarantee for the goods 6 month after delivery date.